

**THE NATIONAL BRICK RESEARCH CENTER**

100 Clemson Research Blvd.  
Anderson, SC 29625  
(864)656-1095



Results of Tests on Brick conducted in accordance with ASTM C67-07 Standard Method for Sampling and Testing



Brick and Structural Clay Tile

04/13/2009



COMPANY INFORMATION	
Name:	Whitacre-Greer Fireproofing Company 1400 South Mahoning Avenue Alliance, OH 44601
Plant:	Whitacre-Greer Fireproofing Company
Sample:	4 x 8 x 2-3/4 50 Series Paver
Lot:	Report #: Product Code:

							Test Date
Compressive Strength	1	2	3	4	5	Average	
<i>psi</i>	9,076	9,580	10,297	9,899	8,789	9,528	04/02/2009
<i>MPa</i>	62.6	66.1	71.0	68.3	60.6	66	

CERTIFICATION	
 Denis Brosnan, Director	 Jim Frederic, Associate Director