

**THE NATIONAL BRICK RESEARCH CENTER**

100 Clemson Research Blvd.  
Anderson, SC 29625  
(864)656-1095



*Results of Tests on Brick conducted in accordance with ASTM C67-07 Standard Method for Sampling and Testing*



*Brick and Structural Clay Tile*

03/24/2009



COMPANY INFORMATION	
Name:	Whitacre-Greer Fireproofing Company 1400 South Mahoning Avenue Alliance, OH 44601
Plant:	Whitacre-Greer Fireproofing Company
Sample:	<b>4 x 8 x 2-3/4 Shade 36 Pavers</b>
Lot:	Report #: Product Code:

							Test Date
Compressive Strength	1	2	3	4	5	Average	
<i>psi</i>	9,443	9,150	9,946	9,735	11,646	9,984	03/24/2009
<i>MPa</i>	65.1	63.1	68.6	67.1	80.3	69	

CERTIFICATION	
 Denis Brosnan, Director	 Jim Frederic, Associate Director