



Product Data Sheet - Refractories February 12, 2007

Product: W-G Low-duty Firebrick Buff
 Plant: Alliance, OH
 Method of Manufacture: Vacuum Dry Press

Typical Chemical Analysis

SiO ₂	63.5%
Al ₂ O ₃	27.6%
Fe ₂ O ₃	2.8%
TiO ₂	1.5%
MgO	0.7%
Alkali	3.5%

Typical Physical Properties

P.C.E. (min)	15
Apparent Porosity	13-17%
Modulus of Rupture (min)	600 psi
Temperature fired to during manufacture = 2000°F (1093°C)	
Manufactured to meet ASTM C 27 (Low Duty) and C 1261	
Recommended maximum operating temperature = 2000°F	

Note: All data subject to reasonable deviation and should not be used as specification.

1400 South Mahoning Ave.
Alliance, Ohio 44601

800 WG PAVER
 P: 330-323.1610
 F: 330-823-5502
 info@wgpavers.com
 www.wgpavers.com